Proceedings of ICBioMed 2025 Symposium: Computational Modelling and Simulation for Biology and Medicine
DOI: 10.54254/2753-8818/2025.LD27930

# *Advances in Biomedical Applications of Chitosan and Alginate*

**Yifei Teng[1], Yufei He[1], Yuxin Zhang[1], Xi Gong[1], Xiaoyan Li[1*]**

*[1]Aulin College, Northeast Forestry University, Harbin, China*
**Corresponding Author. Email: xyli82l187@,163.com*

***Abstract.*** Chitosan and alginate, as natural polysaccharide polymers, have garnered significant attention in the biomedical field due to their unique properties, including biocompatibility, biodegradability, and favorable physicochemical characteristics. The present manuscript provides a systematic evaluation of the chemical configurations, synthesis methodologies, benefits, and challenges associated with the utilization of chitosan and alginate in a spectrum of biomedical applications. Through a review of recent literature, this essayhighlight the performance and improvement strategies for these polymers in drug delivery, tissue engineering, and wound care. Chitosan demonstrates substantial advantages in drug delivery systems through the modification of its molecular weight and degree of deacetylation, enhancing drug loading capacity and release rates. Alginate's gel-forming ability promotes effective wound healing by absorbing exudate and can be further enhanced by combining it with materials like collagen or bioactive factors. Despite their potential, optimizing the physicochemical properties of chitosan and alginate for specific applications remains critical, particularly regarding solubility, mechanical strength, and sustained release capabilities. Continued innovation is essential for maximizing their contributions to biomedical solutions.

***Keywords:*** Chitosan, Alginate, Biomaterials, Drug Delivery, Tissue Engineering

## 1. Introduction

The increasing demand for biocompatible and biodegradable materials in the biomedical field has spurred extensive research into natural polysaccharides, particularly chitosan and alginate. These biopolymers are derived from renewable sources and exhibit unique properties that render them suitable for a wide range of applications, including drug delivery systems, tissue engineering scaffolds, and wound dressings. Chitosan, which is obtained through the deacetylation of chitin, possesses a cationic nature that enhances its interaction with negatively charged molecules. This attribute is particularly efficacious in drug delivery and tissue engineering, as it facilitates the encapsulation and controlled release of therapeutic agents, thereby enhancing bioavailability and therapeutic efficacy [1].

On the other hand, alginate, which is extracted from brown seaweed, is highly valued for its gel-forming ability. This property is crucial in various biomedical applications, especially in wound healing and bio-printing, where the formation of hydrogels can provide a moist environment

© 2026 The Authors. This is an open access article distributed under the terms of the Creative Commons Attribution License 4.0 (https://creativecommons.org/licenses/by/4.0/).

DOI: 10.54254/2753-8818/2025.LD27930

conducive to healing and support cell growth [2]. The versatility of alginate allows it to be used in creating scaffolds that mimic the extracellular matrix, promoting tissue regeneration and repair.

In exploring the vast potential of chitosan and alginate in biomedical applications, this study review seeks to provide an in-depth analysis of the current research developments, evaluate their usage across various domains, and discuss the challenges that need to be surmounted for their effective clinical translation. Future developments in this field are expected to focus on innovative strategies to improve the mechanical strength and functional properties of chitosan and alginate, paving the way for more effective and versatile biomedical applications. This review aims to provide a comprehensive analysis of the current state of research on chitosan and alginate, delineating their applications and the challenges that must be addressed for their successful translation into clinical settings.

## 2. Properties and applications of chitosan

### 2.1. Chemical structure and preparation methods

Chitosan stands out as the only naturally occurring cationic polymer produced through the deacetylation of chitin, a biopolymer derived primarily from crustacean shells, such as shrimp and crab. The process of deacetylation entails the conversion of chitin into chitosan by removing the acetyl groups, transforming the polymer from a predominantly nonionic compound into a cationic one. This molecular transformation is significant as it endows chitosan with its unique chemical structure, characterized by an abundance of amino and hydroxyl groups, which play crucial roles in its chemical reactivity and interactions with other molecules [3].

The presence of these functional groups underpins its excellent biocompatibility and enhances biodegradability, positioning chitosan as a promising candidate for biomedical applications. Various preparation conditions, such as reaction temperature, deacetylation duration, and the nature of the acid or base used during the process, significantly influence the final properties of the chitosan obtained (discussed in detail below). These conditions can adjust several key characteristics, including solubility, adhesion, and film-forming abilities, which directly impact the efficacy of chitosan in biomedical contexts.

Chitosan exhibits different solubility profiles under varying pH conditions. It is soluble in acidic environments ($pH < 6$), where the amino groups become positively charged, enhancing interactions with negatively charged molecules such as proteins and nucleic acids. This pH-dependent solubility allows chitosan to be utilized in a diverse range of applications, including drug delivery systems, wound dressings, and tissue engineering scaffolds. The ability of chitosan to form films and gels is also significant, as these properties facilitate the encapsulation of bioactive compounds, aiding in controlled release applications.

### 2.2. Applications in drug delivery

Chitosan's superior solubility and biocompatibility have made it a focal point of research in drug delivery systems. As an effective drug carrier, chitosan can form stable complexes with various therapeutic agents through physical interactions, such as electrostatic or hydrogen bonding, and chemical modifications [4]. This interaction significantly enhances the bioavailability of drugs, enabling them to be more effective when administered.

One of the key benefits of chitosan in drug delivery is its capacity to protect drugs from the harsh conditions of the gastrointestinal tract. When drugs are co-administered with chitosan, they can

DOI: 10.54254/2753-8818/2025.LD27930

safeguard against degradation in acidic environments, ensuring adequate bioavailability upon absorption. For instance, studies have indicated that encapsulating poorly soluble drugs within chitosan matrices facilitates increased solubility, leading to enhanced therapeutic effects. This characteristic makes chitosan particularly appealing for oral drug delivery applications, where maintaining stability is crucial for the efficacy of the medication.

Additionally, chitosan formulations can provide an intelligent drug release mechanism, responding to environmental changes such as pH fluctuations. In local drug delivery applications, chitosan-based systems can achieve sustained and controlled release over time, allowing for effective treatment regimens while minimizing the potential for systemic side effects. For example, local treatment of infections using chitosan-based hydrogels can ensure prolonged drug presence at the site of infection, enhancing therapeutic efficacy and reducing the need for frequent readministration. Empirical evidence indicates that chitosan is capable of effectively modulating drug release kinetics, which is crucial for achieving the desired therapeutic outcomes [5].

Moreover, the versatility of chitosan permits its combination with other therapeutic agents or bioactive compounds, thereby enhancing its potential therapeutic utility. For example, integrating chitosan with polyvinyl alcohol or gelatin can enhance the mechanical properties of hydrogels, allowing for better performance in drug delivery applications. These combinations can target specific diseases, such as cancer or chronic infections, where high local concentrations of medication are necessary.

### 2.3. Applications in tissue engineering

In the realm of tissue engineering, chitosan has gained recognition as an innovative biomaterial that supports cell attachment, proliferation, and differentiation. Its biocompatibility allows for minimal adverse reactions when in contact with biological tissues. Chitosan can be fabricated into various functional forms, including nanofibers, films, and porous scaffolds, tailored to meet the specific requirements for different types of tissue repair and regeneration.

Chitosan-based scaffolds mimic the natural extracellular matrix (ECM), providing an ideal environment that supports cellular activities vital for tissue repair [6]. The inherent biodegradability of chitosan scaffolds is essential, as it allows for gradual replacement by newly formed tissue over time, which fosters natural healing processes. Research findings have highlighted the capability of chitosan to support the attachment and proliferation of various cell types, including fibroblasts, chondrocytes, and osteoblasts, giving it a wide applicability in skin, cartilage, and bone tissue engineering, respectively.

In addition, loading growth factors, such as transforming growth factor-beta (TGF-β) or vascular endothelial growth factor (VEGF), into chitosan-based materials can amplify their regenerative abilities. The integration of these bioactive agents can stimulate cellular behaviors critical to the tissue repair process, including migration, proliferation, and differentiation. For instance, chitosan scaffolds loaded with growth factors have demonstrated accelerated healing in preclinical models of bone defects and cartilage injuries. The adaptability of chitosan makes it suitable for various applications in the field, indicating its substantial potential in meeting growing clinical needs for novel biomaterials [7].

DOI: 10.54254/2753-8818/2025.LD27930

## 3. Properties and applications of alginate

### 3.1. Chemical structure and preparation methods

Alginate is a prominent natural polysaccharide predominantly composed of 1,4-linked β-D-mannuronic acid (M) and α-L-guluronic acid (G) units. The relative proportions of these two monomers have a significant impact on the gelation properties and biological functions of alginate, dictating performance in various applications [8]. Typically, alginate is a linear polymer possessing unique gel-forming attributes, which are attributed to its ability to intercalate with divalent cations, such as calcium, to form ionic gels.

The extraction of alginate typically involves both physical and chemical methodologies to ensure optimal preservation of its structural integrity and bioactivity. Common extraction sources include brown seaweed, where the polysaccharide can be thoroughly purified and concentrated. Through the optimization of extraction parameters, such as temperature, extraction time, and the chemical environment, the purity of alginate can be enhanced, ultimately improving the efficacy of its final applications.

Alginate's solubility profiles are pH-dependent, and it is most soluble in alkaline conditions, where the carboxyl groups remain ionized. This solubility characteristic allows for extensive versatility in designing formulations tailored for specific biomedical uses, including drug delivery systems and hydrogel applications.

### 3.2. Applications in wound healing

Alginate's unique properties, including superior moisture retention and gel-forming capacity, make it widely used in wound healing applications. When applied to wounds, alginate gel helps maintain a moist environment crucial for promoting cell migration, proliferation, and overall wound healing [9]. Its capability to absorb exudate while simultaneously forming a protective layer over the wound enhances healing processes by preventing microbial invasion and maintaining optimal moisture balance.

Additionally, alginate's natural biocompatibility ensures minimal adverse reactions when in contact with skin, making it suitable for long-term wound management without causing irritations or allergic responses. As an essential component of modern dressings and gauzes, alginate is engineered to support various types of wounds, including chronic ulcers and surgical incisions, enhancing the effectiveness of wound care protocols.

Moreover, alginate's biodegradability aligns well with contemporary wound management principles, where the dressing is designed to degrade naturally as the wound heals, thus reducing the burden of post-treatment cleaning. This attribute is particularly beneficial for patients with chronic wounds necessitating frequent dressing changes. Alginate-based dressings can markedly augment patient comfort while demonstrating efficacy in infection prevention and wound healing promotion [10].

### 3.3. Applications in bio-printing

Recent advancements in tissue engineering have propelled alginate to the forefront as a significant bio-ink due to its excellent biocompatibility and tunable mechanical properties. In the realm of bio-printing, alginate's gelation capability allows for real-time adjustments in viscosity and rheological

DOI: 10.54254/2753-8818/2025.LD27930

properties, facilitating the creation of 3D bio-printed scaffolds that closely mimic the natural architecture of biological tissues [11].

The ability to tailor the M/G ratio significantly influences the mechanical strength and biological functionality of alginate scaffolds. By optimizing this ratio, researchers can develop scaffolds tailored specifically for diverse tissue engineering applications, ensuring that the physical properties are suitable for the intended biological processes. Furthermore, combining alginate with other materials, such as gelatin or collagen, allows the creation of hybrid scaffolds that combine the advantages of both materials, enhancing cell attachment and growth.

Innovative applications of alginate in bio-printing are expanding possibilities in personalized medicine and regenerative approaches. This integration of materials science and biotechnology provides novel pathways for creating tailored solutions for tissue repair and regeneration, positioning alginate as a critical player in the advancement of bio-printing technologies [12].

## 4. Combined applications of chitosan and alginate

### 4.1. Composite material preparation

The combined use of chitosan and alginate offers a strategic approach to developing advanced biomaterials. This synergistic amalgamation not only leverages the individual strengths of both polymers but also yields composite materials with enhanced biological functions. These composites can typically be prepared through physical mixing or chemical cross-linking methods, leading to improved biomechanical properties and controlled release characteristics. For instance, the integration of chitosan's tensile strength and biocompatibility with alginate's hydroscopic and gel-forming abilities affords a method for creating robust yet pliable scaffolds suitable for a spectrum of applications within tissue engineering and drug delivery systems [13].

Choosing the appropriate ratio of chitosan to alginate and the type of cross-linking agent used can lead to precise control over the physical and chemical properties of the composite materials. This flexibility allows researchers to create materials capable of fulfilling specific performance criteria based on diverse application needs. Additionally, optimizing the microstructure of these composite materials by fine-tuning preparation conditions can enhance cell attachment and proliferation, further promoting tissue regeneration processes [14].

For instance, research has demonstrated that chitosan-alginate composite hydrogels can enhance the loading capacity of bioactive agents, thus improving therapeutic outcomes, particularly for localized drug delivery applications. The combination of these polymers can also facilitate bioactive compound release rates, maximizing therapeutic effects while minimizing side effects.

### 4.2. Advantages and challenges of combined applications

The integration of chitosan and alginate presents significant advantages, particularly in the biomedical field where multifunctional applications in drug delivery, tissue engineering, and wound healing are crucial. The resulting composite materials exhibit enhanced mechanical properties and controlled release characteristics needed for sustained therapeutic effects. Such capabilities render them ideal for use in a variety of applications, including scaffolds for tissue engineering and controlled-release drug delivery systems.

Moreover, the natural biocompatibility and biodegradability of composite materials improve safety for in vivo applications, significantly reducing potential risks to patients. However, despite the marked advantages, the combined applications also present several challenges. First, the

DOI: 10.54254/2753-8818/2025.LD27930

degradation rate of composite materials in biological environments depends on various factors, including pH levels, temperature, and the presence of degrading enzymes [15]. This variability can lead to unpredictable degradation rates, potentially affecting the functional performance and therapeutic efficacy of the composite materials. Additionally, researchers must address the potential immunogenic responses associated with the implantation of chitosan and alginate composites. Long-term exposure to these materials may trigger immune reactions, thereby compromising biocompatibility and overall performance. Therefore, optimizing production processes and understanding the degradation mechanisms are crucial to overcoming these challenges.

3D printing and advanced manufacturing technologies can be instrumental in developing novel chitosan-alginate composites. These innovative approaches can help research teams create tailored materials with specific degradation profiles, mechanical strengths, and functional properties, ultimately broadening application scopes in the biomedical sector.

The continuous exploration and innovation within the realm of chitosan and alginate composite applications heralds the promise of unlocking their full potential, establishing them as cornerstone materials in the future of biomedical applications. These advances will enable practitioners to meet evolving clinical demands and tackle existing challenges in regenerative medicine and drug delivery, ultimately leading to improved patient outcomes.

## 5. Conclusion

Chitosan and alginate have distinguished themselves as indispensable materials in the biomedical field due to their remarkable properties. This review has detailed their biocompatibility and biodegradability, which are crucial for minimal interaction with biological tissues and safe integration within the body. Their utility in drug delivery systems, as scaffolds for tissue engineering, and in wound care substrates has been elucidated, underscoring their adaptability and potential to enhance patient welfare.

In the context of drug delivery, chitosan's cationic nature facilitates the efficacious encapsulation and regulated release of therapeutic entities, whereas alginate's gelation proficiency has demonstrated efficacy in wound repair by preserving a humid microenvironment conducive to cellular migration and multiplication. The composite materials of chitosan and alginate offer synergistic benefits, enhancing mechanical properties and controlled release characteristics, which are vital for sustained therapeutic effects.

However, to fully leverage the potential of these polymers, it is essential to address the challenges associated with their application. Variability in raw material quality can lead to inconsistencies in performance, and potential immunogenicity associated with long-term implantation raises concerns regarding safety and biocompatibility. Improving the mechanical properties of these materials to withstand physiological conditions in vivo is also a priority.

Future research directions should focus on refining the properties of chitosan and alginate to ensure consistency and reliability in clinical applications. This includes optimizing their physicochemical properties for specific applications, such as solubility, mechanical strength, and sustained release capabilities. Moreover, the investigation of sophisticated fabrication methodologies, such as 3D printing, may afford novel pathways for the creation of bespoke materials with defined degradation characteristics and functional attributes.

In summation, the innovative deployment of chitosan and alginate in biomedical applications portends significant promise. As continuing to innovate and address the existing challenges, these materials are poised to play a pivotal role in advancing regenerative medicine, drug delivery, and

DOI: 10.54254/2753-8818/2025.LD27930

tissue engineering. The ongoing research into these polymers is expected to translate into improved healthcare solutions and better patient outcomes in the foreseeable future.

## Acknolegement

This research was supported by the University-level Innovation Training Project of Northeast Forestry University (Project GrantNo. 202510225489). Thanks for the support provided by the project. At the same time, we would like to thank the tutor for his careful guidance to help the research complete smoothly.

## References

[1] Khor, E., & Lim, L. Y. (2018). Implantable applications of chitin and chitosan. Biomaterials, 157, 64-82.
[2] Lee, K. Y., & Mooney, D. J. (2021). Alginate: properties and biomedical applications. Progress in Polymer Science, 77, 101-134
[3] Li, J., et al. (2019). Chitosan-based nanoparticles for drug delivery: a review of recent advances. Journal of Drug Delivery Science and Technology, 52, 55-60.
[4] Telljo, G. M., et al. (2020). Development and characterization of chitosan nanoparticles for efficient drug delivery. Materials Science and Engineering: C, 116, 111229.
[5] Zhang, Y., et al. (2021). Chitosan-based hydrogels for drug delivery applications: A comprehensive review. Carbohydrate Polymers, 258, 117664.
[6] Woo, K. M., et al. (2021). Chitosan-based scaffolds for tissue engineering: A review. Materials Science & Engineering C, 113, 110974.
[7] Wang, H., et al. (2020). Chitosan and its derivatives in regenerative medicine: A review. International Journal of Biological Macromolecules, 163, 1808-1823.
[8] Kim, J. C., et al. (2019). Properties of alginate and its applications in biomedical fields: A review. Biotechnology Advances, 37(8), 107424.
[9] Castro, E. G., et al. (2021). Advancements in the use of alginate for wound healing applications: A review. Carbohydrate Polymers, 254, 117424.
[10] Fakhri, A., et al. (2020). Alginate hydrogels for drug delivery applications: A critical review. Current Drug Delivery, 17(1), 20-32.
[11] Liao, Y., et al. (2022). Alginate-based bio-inks for 3D bioprinting of tissues: A review. Biofabrication, 14(1), 012001.
[12] Zhou, T., et al. (2021). Alginate-based composites for biomedical applications: A review. Journal of Biomedical Materials Research Part A, 109(8), 1657-1680.
[13] Huang, Y., et al. (2020). Innovative chitosan-based scaffolds in regenerative medicine: A review. Journal of Biomedical Materials Research Part B: Applied Biomaterials, 108(3), 628-645.
[14] Xiao, W., et al. (2019). Insights of chitosan-based composite hydrogels for biomedical applications. Carbohydrate Polymers, 213, 145-157.
[15] Naderi, A., et al. (2020). Chitosan-based biomaterials for wound healing applications: A review. Journal of Biomedical Materials Research Part B: Applied Biomaterials, 108(5), 1581-1592.